

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 697 135 B1

(12)

EUROPEAN PATENT SPECIFICATION

(45) Date of publication and mention
of the grant of the patent:

27.05.1998 Bulletin 1998/22

(51) Int Cl.⁶: **H01J 29/89**

(86) International application number:
PCT/IB95/00109

(21) Application number: **95907802.3**

(22) Date of filing: **16.02.1995**

(87) International publication number:
WO 95/24053 (08.09.1995 Gazette 1995/38)

(54) **DISPLAY DEVICE COMPRISING A DISPLAY SCREEN PROVIDED WITH A LIGHT-ABSORBING COATING**

**ANZEIGEVORRICHTUNG MIT EINEM MIT EINER LICHT ABSORBIERENDEN SCHICHT
VERSEHENEN BILDSCHIRM**

**UNITE DE VISUALISATION COMPRENANT UN ECRAN POURVU D'UN REVETEMENT
ABSORBANT LA LUMIERE**

(84) Designated Contracting States:
DE ES FR GB IT NL

(30) Priority: **03.03.1994 EP 94200541**

(43) Date of publication of application:
21.02.1996 Bulletin 1996/08

(73) Proprietor: **PHILIPS ELECTRONICS N.V.**
5621 BA Eindhoven (NL)

(72) Inventor: **OOMEN, Emmanuel, Wilhelmus,**
Johannes, Leonardus
NL-5621 BA Eindhoven (NL)

(74) Representative: **Stolk, Steven Adolph**
INTERNATIONAAL OCTROOIBUREAU B.V.,
Prof. Holstlaan 6
5656 AA Eindhoven (NL)

(56) References cited:
EP-A- 0 517 611 EP-A- 0 533 030
EP-A- 0 603 941 US-A- 4 987 338

- **PATENT ABSTRACTS OF JAPAN, Vol. 11, No. 363, E-560; & JP,A,62 136 740 (HITACHI LTD.), 19 June 1987 (19.06.87).**

Note: Within nine months from the publication of the mention of the grant of the European patent, any person may give notice to the European Patent Office of opposition to the European patent granted. Notice of opposition shall be filed in a written reasoned statement. It shall not be deemed to have been filed until the opposition fee has been paid. (Art. 99(1) European Patent Convention).

EP 0 697 135 B1

Description

The invention relates to a display device comprising a display screen which is provided with a light-absorbing coating of an inorganic network comprising at least silicon oxide and a dyestuff.

The invention also relates to a method of manufacturing a light-absorbing coating of an inorganic network comprising at least silicon oxide on a display screen of a display device by means of a sol-gel process, an aqueous solution of an alkoxy silane and a dyestuff being provided on the display screen and heated to convert the solution into said coating.

Light-absorbing coatings which are used to reduce the light transmission are applied to the face plates of display devices, such as cathode ray tubes (CRTs), liquid crystal display devices (LCD and LC-TV) and thin electron displays, to improve the contrast of the image reproduced. By virtue thereof, there is no necessity to change the glass composition of the display screen and the possibilities of bringing the light transmission to a desired value in a simple manner are increased. Such coatings reduce the transmission of both incident ambient light and light originating from CRT phosphors or colour filters. As the coatings can be provided in a uniform manner, the transmission of the filtering layers is also uniform. The incident ambient light passes through the coating and the glass display screen, after which it reflects off, respectively, the rough phosphor layer or the colour filter on the inside of the display screen and again passes through the display screen and the coating. If the transmission of the coating is designated T, the intensity of the reflected ambient light is reduced by a factor of T^2 . Light originating from, respectively, the phosphors and the colour filter passes through the coating only once, so that the intensity of this light is reduced by a factor of T only, resulting in an increase of the contrast by a factor of T. There are transmission or T-coatings the absorption of which is substantially independent of the wavelength of the visible light and which, as a result, are of a neutral-grey colour, and chrominance or C-coatings which selectively absorb one or more spectral regions of the visible light. In the latter case, the absorption is preferably selected so that it takes place in the spectral region situated between the emission spectra of the phosphors.

In United States Patent Specification US 4,987,338 a description is given of a cathode ray tube having a display screen which is provided with a coating comprising a silicon (di)oxide network and a dyestuff having a selective light absorption which is maximal in the wavelength range of 575 ± 20 nm. Said Patent Specification also describes a method of manufacturing such a layer by means of a sol-gel process in which an aqueous alcoholic solution of an alkoxy silane compound, such as tetraethyl orthosilicate $\text{Si}(\text{OC}_2\text{H}_5)_4$ (TEOS), acidified with hydrochloric acid and to which a dyestuff is added, is spin coated onto a display screen. For example,

Rhodamine B is used as the dyestuff. Silicon (di)oxide starts forming in the solution. By a treatment at an increased temperature, the formation of silicon (di)oxide is completed and a layer of a silicon (di)oxide network which also contains the dyestuff is formed.

In the non-prepublished European Patent Application EP-A-603941, filed by Applicants, a description is given of a method of manufacturing a neutral, absorbing coating of silicon oxide, metal oxide and a black dyestuff by means of a sol-gel process, said coating having an improved light fastness and chemical resistance.

A disadvantage of the known method is that the maximally attainable layer thickness of the sol-gel coating is $0.8 \mu\text{m}$ owing to the large quantities of water and alcohol to be evaporated, which leads to shrinkage during the curing operation. Due thereto, the risk of crackles in the layer increases as the layer thickness increases. The maximum concentration of dyestuff in a sol-gel layer is limited. Larger quantities of dyestuff cause the chemical resistance and the mechanical properties of the layer, such as hardness and resistance to wear, to be reduced. This is caused by the fact that the silicon-oxide network is disturbed, which has the additional disadvantage that the dyestuff can be washed out. Owing to the small layer thickness of the known sol-gel layers, the maximum quantity of dyestuff in the layer is limited, so that the maximally attainable light absorption of the layer is limited too. This can be compensated for by means of a second sol-gel layer comprising dyestuff. However, this requires an additional process step.

The known, relatively thin sol-gel layers additionally require a smooth, high-polish display-screen surface in order to obtain a coating having a high-polish surface. This means that the average roughness R_a across the substrate surface must not exceed $0.05 \mu\text{m}$ and that the maximum roughness R_z must not exceed $0.3 \mu\text{m}$. For this purpose, the display-screen surface must be subjected to an expensive fine-polishing treatment, for example with Ce_2O_3 .

It is an object of the invention to provide, *inter alia*, a display device comprising a display screen which is provided with a light-absorbing coating of an inorganic silicon-oxide network, which coating can be applied without inconvenience in a thickness in excess of $0.8 \mu\text{m}$, so that the light absorption attained is higher than that of the known coatings while the concentration of dyestuff in the coating remains the same. The coating must adhere well to the glass display screen and it must be homogeneous and have good optical properties. The coating must also have good mechanical properties, such as a high hardness and a high resistance to wear. It must be possible to apply the coating by means of a sol-gel process. A further object of the invention is to provide a simple method of manufacturing such a coating on a display screen at relatively low temperatures at which no damage is caused to parts of the complete display device, such as a cathode ray tube. In addition, the method must be suitable for the manufacture of a coat-

ing which, if desired, can have a high-polish appearance which does not require a fine-polishing treatment of the display-screen surface.

The object of providing a display device comprising a display screen which is provided with a light-absorbing coating is achieved by a display device, as described in the opening paragraph, which is characterized in accordance with the invention in that a metal oxide of at least one metal selected from the group formed by Al, Ti, Zr and Ge is incorporated into the inorganic network of the coating, and in that the coating also comprises a carbon-containing polymer which is chemically bonded to and intertwined with the inorganic network via Si-C bonds.

The incorporation of an oxide of Al, Ti, Zr and Ge or a mixture of one or more of said metal oxides into the hybrid network of silicon oxide and polymers results in an improved resistance of the coating against leaching out of the dyestuff when the coating is brought into contact with cleaning liquids, such as ethanol, acetone, ammonia and soap solutions. By virtue of said metal oxides, the resistance of the coating against diluted acetic acid and salt water is also improved. The metal oxides also improve the mechanical properties of the coating, such as hardness, resistance to wear and scratch resistance. The coating comprises 1 to 50 mol%, preferably 5 to 35 mol%, of said metal oxide relative to silicon oxide. Below 1 mol%, the favourable effect occurs insufficiently, whereas above 50 mol%, there is no further improvement and the coating becomes unnecessarily expensive. Aluminium oxide is preferred to the other, above-mentioned metal oxides because incorporation of aluminium oxide leads to the best mechanical properties of the coating.

The coating in accordance with the invention is a hybrid inorganic-organic material which comprises a polymeric component in addition to the inorganic network of silicon oxide and metal oxide. In said hybrid material, certain C-atoms of the polymer are chemically bonded to Si atoms of the inorganic network. The polymeric chains are intertwined with the inorganic network, thereby forming a hybrid inorganic-organic network. The chemical bond between the polymeric component and the inorganic network results in coatings which are mechanically strong and thermally stable. By virtue of the polymeric component in the silicon-oxide network, thick coatings up to 100 μm can be manufactured without causing cracks (crackles) in the layer. The bonding between the coating and the glass surfaces is very good.

Examples of polymeric components are polyether, polyacrylate and polyvinyl.

Coatings having thicknesses of from 0.5 to 10 μm are manufactured for display screens. In such relatively thick layers, a relatively large quantity of dyestuff can be dissolved or incorporated, resulting in a low transmission of the layers and hence a high contrast of the image reproduced. In addition, if such relatively thick coatings are used, it is not necessary to subject the glass surface

of the display screen to a time-consuming fine-polishing treatment with, for example, Ce_2O_3 . Rough-polishing of the glass surface with pumice powder to an average roughness (R_a) of 0.13 μm and an R_z value of 1.6 μm yields, in combination with an inventive coating having a thickness of, for example, 2 μm , a high-polish, smooth surface. To obtain an optimum effect, the refractive index of the coating can be adapted to that of the glass of the display screen. The refractive index of the coating can be varied between 1.45 and 1.60. An increase of the concentration of metal oxides in the coating leads to an increase of the refractive index, whereas an increase of the quantity of polymeric component causes the refractive index of the coating to decrease.

The coating in accordance with the invention comprises one or more dyestuffs. Both inorganic pigments and organic dyestuffs are possible. Examples thereof are xanthenes, such as Rhodamine B (Colour Index 45170), phthalocyanines and azo-dyes. Rhodamine B is used to increase the contrast of the display screen, but it gives the coating a violet appearance, which is not always desirable. This can be corrected by adding one or more dyestuffs of a different colour to the coating.


Usually, a neutral grey to black appearance of the coating is desired. For this purpose, a black dyestuff can be used in the coating. A large number of known black dyestuffs are unsuitable because they cannot be dissolved in the sol-gel coating solution to be used. Black dyestuffs which can suitably be used in the coating in accordance with the invention are, *inter alia*, Orasol Black CNTM (Colour Index: Solvent Black 28) and Orasol Black RLTM (Colour Index: Solvent Black 29) by Ciba Geigy; Zapon Black X51TM (Colour Index: Solvent Black 27) by BASF and Lampronol BlackTM (Colour Index: Solvent Black 35) by ICI. These dyestuffs enable high-polish black coatings to be manufactured. A dyestuff which is very suitable is Orasol Black CNTM (Colour Index: Solvent Black 28) because it exhibits a high light fastness. The chemical structural formula of the latter dyestuff is unknown; according to the supplier it is a mono-azo chromium complex. In the wavelength range between 410 and 680 nm, the transmission of the filtering layer comprising Orasol Black CNTM is substantially constant and hence spectrally neutral. Dependent upon the transmission desired, the coating comprises more or less dyestuff or the layer thickness is varied.

If desired, the coating can be provided with anti-static properties by incorporating conductive particles, such as tin-oxide particles which may or may not be doped with Sb or In, conductive ions such as Li^+ or conductive polymers, such as polypyrrole.

The object of providing a simple method of manufacturing a light-absorbing coating of an inorganic network of at least silicon oxide on a display screen of a display device is achieved by a method as described in the opening paragraph, in which the coating is manufactured by providing an aqueous solution of an alkoxysilane and a dyestuff, which solution is subsequently

converted to the coating in a sol-gel process, said meth-
 od in accordance with the invention being characterized
 in that the solution comprises a mixture of

- a trialkoxysilane of the formula:



wherein R is an alkyl group and R¹ is a polymeriz-
 able group, and R¹ is chemically bonded to the Si-
 atom *via* an Si-C bond,

- an alkoxy compound of at least one metal selected
 from the group formed by Al, Ti, Zr and Ge, and
- the dyestuff,

the thermal treatment being carried out to form the dye-
 stuff-containing coating from the inorganic network of
 silicon oxide comprising an oxide of the metal and a pol-
 ymer which is formed from the polymerizable group R¹,
 which polymer is chemically bonded to and intertwined
 with the inorganic network *via* Si-C bonds.

The sol-gel process is based on the homogeneous
 hydrolysis and polycondensation of silicon alkoxides
 and metal alkoxides in the presence of water. A three-
 dimensional, inorganic network is formed by using tri-
 alkoxysilanes and said metal alkoxides. The R-group is
 preferably a C₁-C₅ alkyl group. The trialkoxysilane com-
 prises a polymerizable R¹-group which is chemically
 bonded to the Si-atom *via* an Si-C bond. Examples of
 suitable polymerizable R¹-groups are the epoxy, meth-
 acryloxy and vinyl groups. Suitable examples of trialkox-
 ysilanes comprising polymerizable R¹-groups are:
 3-glycidopropyl-trimethoxysilane, 3-methacryloxy-
 propyl-trimethoxysilane and vinyltriethoxysilane. During
 the sol-gel process, the alkoxysilanes and metal alkox-
 ides hydrolyse and condense to form an inorganic net-
 work of silicon oxide and metal oxide, the polymerizable
 groups forming polymeric chains which are chemically
 bonded to the inorganic network *via* Si-C bonds. The
 epoxy groups, methacryloxy groups and vinyl groups
 polymerize, respectively, into a polyether, a polymeth-
 acrylate and a polyvinyl. The epoxy groups can be ther-
 mally polymerized, for which purpose an amine com-
 pound may optionally be added to the solution as a cat-
 alyst. Polymerization of the other groups requires the
 layer to be exposed to UV light. The polymeric chains
 are chemically bonded to and intertwined with the inor-
 ganic network. This results in mechanically strong and
 thermally stable coatings. The organic polymer provides
 the hybrid material with a large tensile strength, a high
 modulus of elasticity and a high impact resistance, while
 the three-dimensional inorganic network of silicon ox-
 ides and the above-mentioned metal oxides provide the
 material with a high hardness, a high scratch resistance
 and a large compressive strength. The solution compris-
 es 20 to 99 mol%, preferably 30 to 80 mol%, trialkoxysi-
 lane with a polymerizable group relative to the other

alkoxy compounds.

For the metal-alkoxy compounds use is made of
 compounds of the formula:

M(OR)_n, wherein M = Al, Ti, Zr or Ge; R is a C₁-C₅ alkyl
 group and n is the valency of the metal M. Examples of
 suitable metal-alkoxy compounds are:

tetraethoxy-germanate Ge(OC₂H₅)₄ (TEOG),
 tetrabutoxy-zirconate Zr(OC₄H₉)₄ (TBOZ),
 tetrapropoxy-zirconate Zr(OC₃H₇)₄ (TPOZ),
 tripropoxy-aluminate Al(OC₃H₇)₃ (TPOAl),
 tributoxy-aluminate Al(OC₄H₉)₃ (TBOAl) and
 tetraethoxy-titanate Ti(OC₂H₅)₄ (TEOTi).

The solution comprises 1 to 50 mol%, preferably 5
 to 35 mol%, of the metal-alkoxy compound relative to
 the other alkoxy compounds. Hydrolysis and condensa-
 tion cause the corresponding metal oxide to be incorpo-
 rated into the inorganic network. By virtue thereof, the
 above-mentioned advantages as regards chemical re-
 sistance and light fastness of the coating are achieved.
 In addition, the stability of the solution is improved by
 adding said metal-alkoxy compounds, in particular tri-
 alkoxyaluminate.

The solution may also comprise 0.01 to 10 mol% of
 an aminoalkoxysilane, such as 3-aminopropyl-triethox-
 ysilane, or other amine compounds, such as trimethyl-
 amine, relative to the alkoxy compounds. These amine
 compounds serve as a catalyst for the thermal polym-
 erization of the epoxy groups.

One or more of the above-mentioned dyestuffs
 which can be dissolved in the solution, such as the light-
 fast, black dyestuff Orasol Black CN™ (Colour Index:
 Solvent Black 28), can be used as the dyestuff.

The coating can optionally be rendered anti-static
 by adding the above-mentioned conductive compo-
 nents to the solution.

In addition to water for the hydrolysis reaction, the
 solution comprises one or more organic solvents, such
 as ethanol, butanol, isopropanol and diacetone alcohol.

The solution can be customarily provided on the dis-
 play screen, for example, by means of spraying or at-
 omizing. The alcoholic solution is preferably spin coated
 onto the display screen. After drying and heating to, for
 example, 160°C for 30 minutes, a mechanically strong,
 smooth and high-polish filtering layer having the desired
 electrical and light-absorbing properties is obtained.

The formation of a homogeneous, smooth layer can
 be promoted by adding a surface-active substance to
 the solution, for example in quantities of from 0.01 to 5
 wt. %. By virtue of the relatively mild reaction tempera-
 ture, curing of the layer can take place on the display
 screen of a complete display device.

The formed coating of a hybrid, inorganic-organic
 material can be much thicker than 1 µm, for example up
 to 100 µm without causing crackles in the layer. After
 such a coating is spun in a thickness of 2 µm onto rough,
 glass surfaces having an average roughness (R_a) of, for

example, 0.13 μm , said surfaces obtain a smooth, polished appearance. By virtue thereof, an additional fine-polishing treatment of the surface of the glass screen can be dispensed with.

To improve the chemical resistance of the coating, optionally up to 40 mol% of alkyl trialkoxysilane or aryl trialkoxysilane relative to the other alkoxy compounds is added to the coating solution. This addition causes the coating to become more hydrophobic. In this case, the alkoxy groups and the alkyl group comprise 1 to 5 C-atoms. An example of a suitable aryl trialkoxysilane is phenyl-trimethoxysilane. The alkyl and phenyl groups cannot be polymerized.

If desired, a small quantity of a fluorocarbon silane or a silane with another hydrophobic group, such as a hydrocarbon or phenyl group, can be added to the coating solution. The addition of only 0.1 to 1 mol% of a fluorocarbon silane relative to the other alkoxy compounds is sufficient to produce a hydrophobic coating. Owing to the apolar character of the fluorocarbon chain, the fluorocarbon silane settles selectively at the surface of the coating, thereby forming a very thin hydrophobic top coating. This thin top coating has no optical effect. It causes the coating to become water-repellent, so that the dyestuffs can no longer be washed out with aqueous solvents. In addition, visible finger prints can more easily be removed from the coating. A suitable fluorocarbon silane is, for example, $\text{C}_6\text{F}_{13}\text{CH}_2\text{CH}_2\text{-Si}(\text{OC}_2\text{H}_5)_3$. After the sol-gel process, the fluorocarbon chain is chemically bonded to the inorganic network.

A small part of all of the above-mentioned trialkoxysilane compounds can optionally be replaced by the corresponding dialkoxysilane compounds. Dialkoxysilane compounds do not intrinsically lead to a three-dimensional network, but to linear polysiloxane chains. This will lead to a slight reduction of the hardness of the coating.

In a preferred embodiment of the method in accordance with the invention, the coating solution comprises the following constituents:

- alkoxy compounds in the following molar percentages:
 - 40 to 90 mol% 3-glycidoxypropyl-trimethoxysilane
 - 5 to 35 mol% tributoxy-aluminate
 - 0.01 to 10 mol% 3-aminopropyl-triethoxysilane
 - 0 to 30 mol% phenyl-trimethoxysilane
- 1 to 10 wt. % of the black dyestuff with Colour Index Solvent Black 28
- an organic solvent
- water.

It is alternatively possible to apply the coating to a transparent front plate instead of to the display screen itself. This front plate does not have to be made of glass,

but can alternatively be made, for example, of polycarbonate. The coating then also enables the desired scratch resistance to be achieved.

The invention will be explained in greater detail by means of exemplary embodiments and a drawing, in which

the sole Figure is a partly cut-away view of an embodiment of a cathode ray tube in accordance with the invention.

Exemplary embodiment 1.

A quantity of 40 g tributoxy-aluminate is dissolved in 48 g isopropanol to which 21 g ethyl-acetoacetate is added as the complexing agent. This solution is added to a mixture of the following silanes:

- 16 g phenyl-trimethoxysilane
- 120 g 3-glycidoxypropyl-trimethoxysilane
- 9 g 3-aminopropyl-triethoxysilane

Subsequently, 100 g isopropanol and 100 g diacetone alcohol are admixed. The mixture is then hydrolysed by adding water step-by-step until the stoichiometric quantity of water has been added; meanwhile the mixture is cooled by means of an ice bath. After all the water has been added, the solution is stirred at room temperature for 2 hours. Subsequently, the dyestuff Orasol Black CNTM (Colour Index: Solvent Black 28) is added in a concentration of 6 g per kilogram of liquid, whereafter the solution is filtrated.

The solution obtained comprises alkoxy compounds in the following molar percentages:

- 10 mol% phenyl-trimethoxysilane
- 65 mol% 3-glycidoxypropyl-trimethoxysilane
- 5 mol% 3-aminopropyl-triethoxysilane
- 20 mol% tributoxy-aluminate.

The solution obtained is subsequently spin coated onto a flat display screen at a rate of 200 r.p.m., whereafter it is cured for 1 hour at 160° C. The coating obtained has a thickness of 4 μm . Said high-polish, neutral-black coating exhibits an average transmission of $20 \pm 2\%$ between 420 and 680 nm.

The thickness of the filtering layer obtained is governed, *inter alia*, by the quantity of solvent and the number of revolutions during spin coating of the layer.

The coating is resistant to washing with a weak acid, weak base, ethanol, acetone, water and customary cleaning agents.

The adhesion of the coating to the surface complies with the tape-test requirements.

In a scratch-resistance test in which a conical diamond (radius 8 μm) is moved over the surface with a force of 45 g, it is established that any scratches formed are invisible to the naked eye.

The hardness is tested by means of a pencil test, in

which pencils of different hardnesses to which a force of 7.5 N is applied are moved over the surface of the layer at an angle of 45° and a rate of 0.05 m/s. According to this test, the coating in accordance with the invention has a degree of hardness in the range from 7 H to 8 H.

The abrasion resistance of the coating is determined by rubbing the same surface of the layer twenty times over a length of 25 mm with a Lion 50-50 eraser with a force of 10 N. The outcome of the test is that any scratches on the rubbed surface are invisible to the naked eye.

The light fastness of the coating is tested by means of the so-called Xeno test in accordance with DIN-standards 54003 and 54004, using a Heraeus Sun test CPS apparatus. In this test, the coating is exposed to artificial light corresponding to daylight under indoor conditions, in such a manner that a residence time of the filtering layer of 24 hours in this apparatus corresponds to 1 year of indoor conditions as tested according to DIN-wool standards. After an exposure time corresponding to 4 years of indoor use (DIN-wool scale 6) the transmission of the layer has increased by 10% only.

Exemplary embodiment 2.

The Figure is a diagrammatic, cut-away view of a cathode ray tube 1 which is known *per se* and which has a glass envelope 2 comprising a display screen 3, a cone 4 and a neck 5. In the neck there is provided an electron gun 6 for generating an electron beam. This electron beam is focused on a phosphor layer on the inside 7 of the display screen 3. The electron beam is deflected across the display screen in two mutually perpendicular directions by means of a deflection coil system. The display screen 3 is provided on the outside with a light-absorbing coating 8 in accordance with the invention.


The invention enables light-absorbing coatings having a thickness of at least 0.5 µm and having a low transmission to be provided on a display screen of a display device in a simple manner. These relatively thick layers do not exhibit crackles. A high-polish coating can be obtained even if, prior to the application of the coating, the display screen has a matt appearance with an average roughness R_a of 0.13 µm. The average roughness R_a of the coated display screen is 0.03 µm. The coatings are lightfast and resistant to customary cleaning liquids. Curing of the filtering layer at 160° C, to which temperature display tubes are resistant, results in scratch-resistant and wear-resistant layers.

Claims

1. A display device comprising a display screen which is provided with a light-absorbing coating of an inorganic network comprising at least silicon oxide and a dyestuff, characterized in that a metal oxide

of at least one metal selected from the group formed by Al, Ti, Zr and Ge is incorporated into the network, and in that the coating also comprises a carbon-containing polymer which is chemically bonded to the inorganic network via Si-C bonds.

2. A display device as claimed in Claim 1, characterized in that the thickness of the coating is 0.8 to 10 µm.
3. A display device as claimed in Claim 1, characterized in that the coating comprises 5 to 35 mol% aluminium relative to silicon.
4. A display device as claimed in Claim 1, characterized in that the polymer is selected from the group formed by polyether, polyacrylate and polyvinyl.
5. A display device as claimed in Claim 1, characterized in that the black dyestuff with Colour Index Solvent Black 28 is used as the dyestuff.
6. A method of manufacturing a light-absorbing coating of an inorganic network of at least silicon oxide on a display screen of a display device by means of a sol-gel process, in which an aqueous solution of an alkoxysilane and a dyestuff is provided on the display screen and heated to convert the solution into said coating, characterized in that the solution comprises a mixture of
 - a trialkoxysilane of the formula:



wherein R is an alkyl group and R^1 is a polymerizable group, and in which R^1 is chemically bonded to the Si-atom via a Si-C bond,

- an alkoxy compound of at least one metal selected from the group formed by Al, Ti, Zr and Ge, and
- the dyestuff,

the thermal treatment being carried out to form the dyestuff-containing coating from the inorganic network of silicon oxide comprising an oxide of the metal and a polymer which is formed from the polymerizable R^1 -group, which polymer is chemically bonded to and intertwined with the inorganic network via Si-C bonds.


7. A method as claimed in Claim 6, characterized in that the polymerizable group is selected from the group formed by epoxy, methacryloxy and vinyl.
8. A method as claimed in Claim 6, characterized in that trialkoxyaluminate is used as the metal alkoxy

- compound.
9. A method as claimed in Claim 6, characterized in that the black dyestuff with Colour Index Solvent Black 28 is used as the dyestuff.
 10. A method as claimed in Claim 6, characterized in that the solution also comprises 40 mol% alkyl trialkoxysilane or aryl trialkoxysilane relative to the other alkoxy compounds.
 11. A method as claimed in Claim 6, characterized in that the solution also comprises 1 mol% of a fluorocarbon silane relative to the other alkoxy compounds.
 12. A method as claimed in Claim 6, characterized in that the solution comprises the following constituents:
 - alkoxy compounds in the following molar percentages:
 - 40 to 90 mol% 3-glycidoxypropyl-trimethoxysilane
 - 5 to 35 mol% tributoxy-aluminate
 - 0.01 to 10 mol% 3-aminopropyl-triethoxysilane
 - 0 to 30 mol% phenyl-trimethoxysilane
 - 1 to 10 wt. % of the black dyestuff with Colour Index Solvent Black 28
 - an organic solvent
 - water.
 13. A method as claimed in Claim 6, characterized in that the solution is spin coated onto the display screen.

Patentansprüche

1. Bildwiedergabeeinrichtung mit einem Bildschirm mit einer lichtschluckenden Schicht aus einem anorganischen Netzwerk mit mindestens Siliziumoxid und mit einem Farbstoff, dadurch gekennzeichnet, daß in dem anorganischen Netzwerk der Deckschicht ein Metalloxid eingebaut ist, aus mindestens einem Metall, gewählt aus der Gruppe, gebildet durch Al, Ti, Zr und Ge, und daß die Deckschicht zugleich ein kohlenstoffhaltiges Polymer aufweist, das über Si-C-Bindungen mit dem anorganischen Netzwerk chemisch gebunden ist.
2. Bildwiedergabeeinrichtung nach Anspruch 1, dadurch gekennzeichnet, daß die Dicke der Deckschicht 0,8 bis 10 µm beträgt.

3. Bildwiedergabeeinrichtung nach Anspruch 1, dadurch gekennzeichnet, daß die Deckschicht 5 bis 35 mol% Aluminium gegenüber Silizium aufweist.
4. Bildwiedergabeeinrichtung nach Anspruch 1, dadurch gekennzeichnet, daß das Polymer aus der Gruppe gewählt ist, die durch Polyäther, Polycarbonat und Polyvinyl gebildet wird.
5. Bildwiedergabeeinrichtung nach Anspruch 1, dadurch gekennzeichnet, daß der schwarze Farbstoff mit Colour Index Solvent Black 28 als Farbstoff verwendet wird.
6. Verfahren zum Herstellen einer lichtschluckenden Deckschicht aus einem anorganischen Netzwerk mit wenigstens Siliziumoxid auf einem Bildschirm einer Bildwiedergabeeinrichtung mittels eines Sol-Gel-Prozesses, wobei eine wässrige Lösung eines Alkoxysilans und eines Farbstoffs auf dem Bildschirm angebracht und durch Erwärmung in die Deckschicht umgewandelt wird, dadurch gekennzeichnet, daß die Lösung ein Gemisch aus den nachfolgenden Stoffen aufweist:
 - einem Trialkoxysilan mit der Formel:



wobei R eine Alkylgruppe und R¹ eine polymerisierbare Gruppe darstellt und wobei R¹ über eine Si-C-Bindung an dem Si-Atom chemisch gebunden ist,

- einer Alkoxyverbindung aus mindestens einem Metall, gewählt aus der Gruppe, die durch Al, Ti, Zr und Ge gebildet ist, und
- dem Farbstoff,

wobei durch die Wärmebehandlung die den Farbstoff enthaltende Deckschicht aus dem anorganischen Netzwerk aus Siliziumoxid und einem darin eingebauten Oxid des Metalls gebildet wird, sowie aus einem Polymer, gebildet aus der polymerisierbaren Gruppe R¹, wobei dieses Polymer über Si-C-Bindungen an dem anorganischen Netzwerk chemisch gebunden und damit verflochten ist.

7. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die polymerisierbare Gruppe gewählt wird aus der Gruppe, die durch Epoxy, Methacryloxy und Vinyl gebildet ist.
8. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß als Metallalkoxyverbindung Trialkoxyaluminat verwendet wird.
9. Verfahren nach Anspruch 6, dadurch gekennzeichnet,

- net, daß als Farbstoff der schwarze Farbstoff mit Colour Index Solvent Black 28 verwendet wird.
10. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die Lösung zugleich 40 mol% Alkyltrialkoxysilan oder Aryltrialkoxysilan gegenüber den übrigen Alkoxyverbindungen aufweist. 5
11. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die Lösung zugleich bis zu 1 mol% eines Kohlenfluorsilans gegenüber den weiteren Alkoxyverbindungen aufweist. 10
12. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die Lösung die nachfolgenden Bestandteile aufweist: 15
- Alkoxyverbindungen mit den untenstehenden molaren Prozentsätzen: 20
 - 40 bis 90 mol% 3-Glycidoxypolytrimethoxysilan
 - 5 bis 35 mol% Tributoxyaluminat
 - 0,01 bis 10 mol% 3-Aminopropyltriäthoxysilan 25
 - 0 bis 30 mol% Phenyltrimethoxysilan
 - 1 bis 10 Gew.% des schwarzen Farbstoffs mit Colour Index Solvent Black 28
 - ein organisches Lösungsmittel 30
 - Wasser.
13. Verfahren nach Anspruch 6, dadurch gekennzeichnet, daß die Lösung im Schleuderverfahren auf dem Bildschirm angebracht wird. 35

Revendications


1. Dispositif d'affichage comprenant un écran d'affichage qui est pourvu d'un revêtement absorbant la lumière d'un réseau inorganique comprenant au moins de l'oxyde de silicium et une matière colorante, caractérisé en ce qu'un oxyde métallique d'au moins un métal sélectionné dans le groupe formé par l'Al, le Ti, le Zr et le Ge est incorporé dans le réseau, et en ce que le revêtement comprend également un polymère contenant du carbone qui est lié chimiquement au réseau inorganique via des liaisons Si-C. 40
2. Dispositif d'affichage suivant la revendication 1, caractérisé en ce que l'épaisseur du revêtement est comprise entre 0,8 et 10 µm. 45
3. Dispositif d'affichage suivant la revendication 1, caractérisé en ce que le revêtement comprend 5 à 35% en mole d'aluminium par rapport au silicium. 50

4. Dispositif d'affichage suivant la revendication 1, caractérisé en ce que le polymère est sélectionné dans le groupe formé par les polyéthers, les polyacrylates et les polyvinyles.

5. Dispositif d'affichage suivant la revendication 1, caractérisé en ce qu'on utilise comme matière colorante la matière colorante noire avec l'indice de couleur : Noir Solvant 28.

6. Procédé de fabrication d'un revêtement absorbant la lumière d'un réseau inorganique au moins d'oxyde de silicium sur un écran d'affichage d'un dispositif d'affichage au moyen d'un processus sol-gel, au cours duquel une solution aqueuse d'un alcoxysilane et d'une matière colorante est déposée sur l'écran d'affichage et chauffée de manière à convertir la solution en revêtement, caractérisé en ce que la solution comprend un mélange

- d'un trialcoxysilane de la formule :



où R est un groupe alkyle et R¹ est un groupe polymérisable, et où R¹ est lié chimiquement à l'atome de Si via une liaison Si-C,

- d'un composé alcoxy d'au moins un métal sélectionné dans le groupe formé par l'Al, le Ti, le Zr et le Ge, et
- de la matière colorante,

le traitement thermique étant effectué de manière à former le revêtement contenant la matière colorante à partir du réseau inorganique d'oxyde de silicium comprenant un oxyde du métal et un polymère qui est formé à partir du groupe R¹ polymérisable, lequel polymère est lié chimiquement au réseau inorganique et entrelacé avec ce dernier via des liaisons Si-C.

7. Procédé suivant la revendication 6, caractérisé en ce que le groupe polymérisable est sélectionné dans le groupe formé par les époxy, méthacryloxy et vinyloxy.

8. Procédé suivant la revendication 6, caractérisé en ce qu'on utilise comme composé alcoxy métallique du trialcoxyaluminate.

9. Procédé suivant la revendication 6, caractérisé en ce qu'on utilise comme matière colorante la matière colorante noire avec l'indice de couleur : Noir Solvant 28.

10. Procédé suivant la revendication 6, caractérisé en ce que la solution comprend également 40% en mo-

le de alkyltrialcoxysilane ou de aryltrialcoxysilane
par rapport aux autres composés alcoxy.

11. Procédé suivant la revendication 6, caractérisé en
ce que la solution comprend également 1% en mole 5
d'un silane fluorocarboné par rapport aux autres
composés alcoxy.

12. Procédé suivant la revendication 6, caractérisé en
ce que la solution comprend les constituants 10
suivants :

- des composés alcoxy dans les pourcentages
molaires suivants : 15
 - 40 à 90% en mole de 3-glycidoxypropyltri-
méthoxysilane
 - 5 à 35% en mole de tributoxyaluminate
 - 0,01 à 10% en mole de 3-aminopropyl trié-
thoxysilane 20
 - 0 à 30% en mole de phénylméthoxysilane
- 1 à 10% en poids de matière colorante noire
avec un indice de couleur : Noir Solvant 28
- un solvant organique 25
- de l'eau.

13. Procédé suivant la revendication 6, caractérisé en
ce que la solution est appliquée par centrifugation
sur l'écran d'affichage. 30

35

40

45

50

55

